

Superconducting band stabilizing superconductivity in MgB_2

Ekkehard Krüger

Institut für Metallkunde, 2. Lehrstuhl, Universität Stuttgart, D-70569 Stuttgart, Germany

It is shown that the superconducting intermetallic compound MgB_2 possesses a narrow, partly filled “superconducting band” with Wannier functions of special symmetry in its band structure. This result corroborates previous observations about the band structures of numerous superconductors and non-superconductors showing that evidently superconductivity is always connected with such superconducting bands. These findings are interpreted in the framework of a nonadiabatic extension of the Heisenberg model. Within this new group-theoretical model of correlated systems, Cooper pairs are stabilized by a nonadiabatic mechanism of constraining forces effective in narrow superconducting bands. The formation of Cooper pairs in a superconducting band is mediated by the energetically lowest boson excitations in the considered material that carry the crystal spin-angular momentum $1 \cdot \hbar$. These crystal-spin-1 bosons are proposed to determine whether the material is a conventional low- T_c or a high- T_c superconductor. This interpretation provides the electron-phonon mechanism that enters the BCS theory in conventional superconductors.

Keywords: occurrence of superconductivity, superconducting band, correlated electrons, nonadiabatic Heisenberg model, group theory

1. INTRODUCTION

In a former paper [1] the author proposed to generalize the classical Heisenberg model of magnetism [2] by introducing three new postulates emphasizing the *atomic-like* motion of electrons in narrow, partly filled energy bands. The resulting “nonadiabatic Heisenberg model” (NHM) uses the term “atomic-like motion” in the sense of Mott [3] and Hubbard[4]: as long as possible the electrons occupy localized states and perform their band motion by hopping from one atom to another.

This group-theoretical model provides a novel concept to understand correlation effects in narrow bands in terms of symmetry-adapted Wannier functions and was developed to interpret the existence of magnetic and superconducting bands with Wannier functions of special symmetries in the band structures of magnetic and superconducting materials.

Evidently, the magnetic states in Cr [5], Fe [6], La_2CuO_4 [7], and $\text{YBa}_2\text{Cu}_3\text{O}_6$ [8] are connected with narrow, partly filled magnetic bands in the band structures of the respective materials. Superconducting bands (as shall be defined in Sec. 3.1) have already been identified in the band structures of numerous elemental superconductors [9] and of the high-temperature superconductors La_2CuO_4 [7] and $\text{YBa}_2\text{Cu}_3\text{O}_7$ [10]. Furthermore, partly filled superconducting bands cannot be found in those elemental metals (such as Li, Na, K, Rb, Cs, Ca, Cu, Ag, and Au) which do not become superconducting [9]. An investigation into the band structures of the transition metals in terms of superconducting bands straightforwardly leads to the Matthias rule [11].

The aim of the present paper is to show that the intermetallic compound MgB_2 with the relatively high transition temperature $T_c \approx 39\text{K}$ [12] possesses a narrow, partly filled superconducting band in its band structure. Before in Sec. 4 the existence of this band shall be established, the following Sec. 2 outlines the physical sub-

stance of the new nonadiabatic model and Sec. 3 gives the definition of superconducting bands and a short characterization of the mechanism of Cooper pair formation in these bands.

2. NONADIABATIC HEISENBERG MODEL

In this section the nonadiabatic Heisenberg model is shortly characterized, a detailed substantiation of all the statements is given in Ref. [1].

Within the NHM, the Hamiltonian

$$H^n = H_{HF} + H_{Cb}^n \quad (2.1)$$

in a partly filled superconducting or magnetic band consists of the familiar Hartree-Fock operator H_{HF} and the nonadiabatic Coulomb interaction

$$H_{Cb}^n = \sum_{\mathbf{T}, m} \langle \mathbf{T}_1, m_1, n; \mathbf{T}_2, m_2, n | H_{Cb} | \mathbf{T}'_1, m'_1, n; \mathbf{T}'_2, m'_2, n \rangle \times c_{\mathbf{T}_1 m_1}^{n\dagger} c_{\mathbf{T}_2 m_2}^{n\dagger} c_{\mathbf{T}'_2 m'_2}^n c_{\mathbf{T}'_1 m'_1}^n. \quad (2.2)$$

The fermion operators $c_{\mathbf{T}m}^{n\dagger}$ and $c_{\mathbf{T}m}^n$ create and annihilate electrons in “nonadiabatic localized states” $|\mathbf{T}, m, n\rangle$ [with crystal spin m (see Sec. 2.1.3) on the atom at position $\mathbf{T}$] that depend on an additional quantum number n labeling different states of the nonadiabatic motion of the center of mass of the localized states [13]. The matrix elements of H_{Cb}^n are integrals over nonadiabatic localized functions as given in Eq. (2.17) of Ref. [1].

The introduction of these nonadiabatic localized states allows a realistic description of an atomic-like motion of the electrons. While in the framework of the adiabatic approximation the electrons move in *rigid* orbitals in the *average* potential of the other electrons, in the nonadiabatic system a localized electron moves in a potential depending on which of the adjacent localized states is occupied and on the present motion of the electrons in

these states. Such a correlated electronic motion within a fluctuating potential leads to localized orbitals which are not symmetric at any moment, but only on the average of time. As a consequence, the centers of mass of the localized states become permanently accelerated in varying directions. The resulting nonadiabatic motions of the centers of mass are labeled by the new quantum number n .

The NHM assumes that there exist nonadiabatic localized states satisfying the equation

$$\langle \mathbf{T}_1, m_1, n; \mathbf{T}_2, m_2, n | H_{Cb} | \mathbf{T}'_1, m'_1, n; \mathbf{T}'_2, m'_2, n \rangle = 0 \quad (2.3)$$

for

$$\{\mathbf{T}_1, \mathbf{T}_2\} \neq \{\mathbf{T}'_1, \mathbf{T}'_2\} \quad (2.4)$$

if the considered partly filled band is one of the narrowest bands of the given material, where $\{\mathbf{T}_1, \mathbf{T}_2\} = \{\mathbf{T}'_1, \mathbf{T}'_2\}$ means $\mathbf{T}_1 = \mathbf{T}'_1$ and $\mathbf{T}_2 = \mathbf{T}'_2$ or $\mathbf{T}_1 = \mathbf{T}'_2$ and $\mathbf{T}_2 = \mathbf{T}'_1$.

This Eq. (2.3) follows from the first postulate of the NHM which assumes that the correlation effects specified by Eq. (2.4) are energetically unfavorable in narrow, partly filled bands. So the electrons modify their localized orbitals within the nonadiabatic localized states in such a way that the transitions specified by Eq. (2.4) do not occur. These modified electronic orbitals yield a well-defined motion of the centers of mass labeled by the quantum number n .

Eq. (2.3) defines the “atomic-like state of motion” within the NHM and replaces the stronger Heisenberg condition claiming that in narrow, half-filled bands there is exactly one electron on each atom.

2.1. Novel features of the nonadiabatic Heisenberg model

A correlated electron system characterized by Eq. (2.3) possesses three novel features distinguishing it from any system described within the adiabatic approximation. First, within the NHM there exists a “nonadiabatic condensation energy” ΔE ; second, the nonadiabatic Hamiltonian H^n possesses unusual commutation properties; and thirdly, the “crystal spin” of the nonadiabatic localized states is a conserved quantity.

2.1.1. Nonadiabatic condensation energy

Eq. (2.3) is assumed to be satisfied in the *ground state* of the narrowest, partly filled bands of the metals. Since this equation is clearly not true within the adiabatic approximation, the Coulomb correlation energy of the nonadiabatic atomic-like state characterized by Eq. (2.3) is lower than the correlation energy of this state within the adiabatic approximation. Hence, the electrons of the narrowest, partly filled bands of the metals lower their

energy by the “nonadiabatic condensation energy”

$$\Delta E = E_b - E_a \quad (2.5)$$

at the transition from the adiabatic (more bandlike) to the nonadiabatic atomic-like state. E_a and E_b denote the ground-state energies of the operator H^n in Eq. (2.1) and of the related operator within the adiabatic approximation, respectively. ΔE may be approximated by Eq. (2.20) of Ref. [1].

2.1.2. Commutation properties of the nonadiabatic Hamiltonian H^n

In superconducting and magnetic bands the symmetry of the nonadiabatic localized states is not adapted to the space group G of the considered material, but only to a subgroup M of G . As a consequence of Eq. (2.3), the nonadiabatic Hamiltonian H^n in Eq. (2.1) commutes with all the symmetry operators of M , *but not* with the symmetry operators of G that do not belong to M . Thus, the group-theoretical NHM allows a straightforward physical interpretation of the symmetry of the localized states related to the atomic-like motion in narrow, partly filled bands.

This feature distinguishes H^n from any Hamiltonian H written in the adiabatic approximation since the symmetry properties of H are independent of the symmetry of the Wannier basis used to calculate its matrix elements.

2.1.3. Crystal-spin angular momentum

The nonadiabatic localized states are no longer labeled by the spin quantum number $s = \pm \frac{1}{2}$, but by a new quantum number $m = \pm \frac{1}{2}$ which may be called the quantum number of the “crystal spin”. This is in analogy to the wave vector $\mathbf{k}$ of the Bloch functions which is sometimes referred to as “crystal momentum” in order to distinguish it from a true momentum.

Within the nonadiabatic correlated system the conservation law of spin angular momentum as expressed by the equation

$$[H, S(\alpha)] = 0 \quad \text{for } \alpha \in O(3) \quad (2.6)$$

is replaced by the conservation law

$$[H^n, M(\alpha)] = 0 \quad \text{for } \alpha \in G_M \quad (2.7)$$

of the crystal spin m . The operators $S(\alpha)$ are the symmetry operators of the electron spin and $O(3)$ stands for the three-dimensional rotation group; $M(\alpha)$ and G_M denote the analogous operators and the corresponding group, respectively, in the space group of the considered material.

At interactions of the electrons with phonons, a Bloch state bears the crystal-spin angular momentum $m = \frac{1}{2} \cdot \hbar$ and suitable linear combinations of the phonons carry the crystal spin $m = 1 \cdot \hbar$.

2.2. Superconducting and magnetic bands

Localized functions $\langle \mathbf{r}, t, \mathbf{q} | \mathbf{T}, m, n \rangle$ representing the nonadiabatic localized states are highly complicated since they depend on an additional coordinate $\mathbf{q}$ related to the nonadiabatic motion of the center of mass (while $\mathbf{r}$ and t denote, as usual, the local and spin coordinate, respectively, of the localized electron). Fortunately, these functions need not to be known. The NHM only postulates their existence and assumes that they have the same symmetry and spin dependence as the best localized exact Wannier functions of the considered partly filled energy band. In this context, “exact Wannier functions” form a *complete* basis of the Bloch functions of this band.

In several narrow, partly filled energy bands of the metals the electrons can gain the nonadiabatic condensation energy ΔE only under specific conditions: in a narrow, partly filled “magnetic band” [1, 8] related to a magnetic structure S the electrons can occupy the atomic-like state *only if* this magnetic structure S actually exists in the considered material. Further, electrons in a narrow, partly filled “superconducting band” (as defined in Sec. 3.1) occupying the atomic-like state are forced in a new way to form Cooper pairs below a certain transition temperature. This “new way” will be substantiated in Sec. 3.2.

This result suggests that the nonadiabatic condensation energy ΔE in Eq. (2.5) stabilizes both magnetism [5, 6] and superconductivity [14, 15]. Both phenomena have the same physical origin: they exist because the electrons at the Fermi level tend to occupy the energetically favorable atomic-like state. The special symmetry and spin dependence of the related Wannier function determine whether the material becomes magnetic or superconducting (or has a property not yet considered). This important statement of the NHM is corroborated by the calculated band structures mentioned in Sec. 1.

3. SUPERCONDUCTING BANDS AND SUPERCONDUCTIVITY

3.1. Definition of superconducting bands

Usually, the energy bands crossing the Fermi level in the paramagnetic metals are degenerate at several points and lines of symmetry of the Brillouin zone. Therefore, it is not possible to separate narrow isolated sets of bands whose Bloch functions can be unitarily transformed into best localized Wannier functions that are symmetry-adapted to the full space group G of the considered metal. However, in some cases such Wannier functions may be constructed if we allow that they are adapted only to the symmetry of a magnetic subgroup M of G or if they are allowed to be spin dependent [1]. In the first case, the band is a magnetic band as mentioned in the foregoing Sec. 2.2, in the second case it is a superconducting band.

We define an energy band of a given material to be a “superconducting band” if the Bloch functions of this band can be unitarily transformed into *spin-dependent* Wannier functions $w_{im}(\mathbf{r} - \mathbf{R} - \boldsymbol{\rho}_i, t)$ (as defined by Eq. (A22) of Ref. [1]) which are

- centered on a (well-defined) part of the atoms (at positions $\mathbf{T} = \mathbf{R} + \boldsymbol{\rho}_i$);
- symmetry-adapted to the (full) space group G of this material;
- labeled by the quantum number $m = \pm \frac{1}{2}$ of the crystal spin [see note (ii) of Table IV]; and
- localized as well as possible.

3.2. Mechanism of Cooper pair formation in a superconducting band

In a narrow, roughly half-filled superconducting band, the electron system has no other possibility to gain the nonadiabatic condensation energy ΔE in Eq. (2.5) but to occupy an atomic-like state represented by *spin-dependent* Wannier functions. This spin dependence has far reaching consequences because only special atomic-like motions with spin-dependent localized states may exist in the nonadiabatic system. These states are determined by the interplay of two conservation laws: on the one hand, the bare electrons satisfy the conservation of the electron spin and, on the other hand, the nonadiabatic localized states conserve the crystal spin.

In this section, the atomic-like motion with spin-dependent localized states is shortly characterized, a detailed substantiation of all the statements is given in Ref. [15].

3.2.1. Nonadiabatic atomic-like motion with spin-dependent localized states

When the localized states are represented by spin-dependent Wannier functions, the nonadiabatic operator H_{Cb}^n of Coulomb interaction complying with Eq. (2.3) does not conserve the crystal spin angular momentum, i.e.,

$$[H_{Cb}^n, M(\alpha)] \neq 0 \quad (3.1)$$

for at least one $\alpha \in G_M$. At first sight, this result seems to show that the NHM is not applicable to superconducting bands. However, the nonadiabatic motion of the centers of mass in the localized states gives point to another interpretation. Remember that the quantum number n in Eq. (2.3) labels the special nonadiabatic motion of the centers of mass of those localized states which satisfy this Eq. (2.3). Thus, Eq. (3.1) indicates that this special nonadiabatic motion occurs in such a way that phonons or other boson excitation are excited (or absorbed) which




FIG. 1: Band structure of MgB₂ as calculated by Ove Jepsen [16] with symmetry labels as given in Table I. The bold line shows the superconducting band. It is related to the B atoms and consists of two branches because there are two B atoms in the unit cell.

store the surplus crystal spin angular momenta. This interpretation is corroborated by the fact that by the mere addition of symmetrized boson operators we may construct from H_{Cb}^n an interaction

$$H_{Cb}^{ns} = \sum_{\mathbf{T}, m} \langle \mathbf{T}'_1, l_1; \mathbf{T}'_2, l_2; \mathbf{T}_1, m_1, n; \mathbf{T}_2, m_2, n | H_{Cb} | \mathbf{T}_1, m'_1, n; \mathbf{T}_2, m'_2, n \rangle b_{\mathbf{T}'_1 l_1}^\dagger b_{\mathbf{T}'_2 l_2}^\dagger \times c_{\mathbf{T}_1 m_1}^{n\dagger} c_{\mathbf{T}_2 m_2}^{n\dagger} c_{\mathbf{T}_2 m'_2}^n c_{\mathbf{T}_1 m'_1}^n + \text{H.c.} \quad (3.2)$$

which conserves the crystal spin,

$$[H_{Cb}^{ns}, M(\alpha)] = 0 \quad \text{for } \alpha \in G_M. \quad (3.3)$$

The boson operator $b_{\mathbf{T}l}^\dagger$ creates a localized boson $|\mathbf{T}, l\rangle$ with crystal spin $l = -1, 0, +1$ at the position $\mathbf{T}$.

This “spin-boson interaction” H_{Cb}^{ns} replaces the Coulomb interaction H_{Cb}^n in a narrow superconducting band. In cubic crystals the matrix elements of H_{Cb}^{ns} are determined by Eq. (4.28) of Ref. [14]. The complete nonadiabatic Hamiltonian H^n now may be written as

$$H^n = H_{HF} + H_{Cb}^{ns} + H_b \quad (3.4)$$

with H_b denoting the operator of the boson energy.

3.2.2. Atomic-like motion with spin-dependent localized states at zero temperature

Since H_{Cb}^{ns} depends on boson operators, a certain number of crystal-spin-1 bosons is excited in the ground state of the nonadiabatic Hamiltonian H^n at any temperature. However, at zero temperature we may assume that these bosons are virtually excited, i.e., each boson pair is re-absorbed immediately after its generation, producing in this way an effective *electron-electron* interaction. Thus, at zero temperature we approximate the nonadiabatic system represented by H^n by a purely electronic system represented by a Hamiltonian

$$H^0 = H_{HF} + H_{Cb}^0 \quad (3.5)$$

not depending on boson operators.

Also at zero temperature, the nonadiabatic mechanism specified by Eq. (2.3) occurs in the nonadiabatic system. In the purely electronic system represented by H^0 , however, the electronic motion is no longer coupled to the motion of the centers of mass of the localized states, but the interaction term H_{Cb}^0 of H^0 contains the effective electron-electron interaction which is produced by this nonadiabatic mechanism. Thus, the matrix elements of H_{Cb}^0 do not follow Eq. (2.3) and the system represented by H^0 can be described within the adiabatic approximation. The localized states related to the atomic-like motion now are represented by adiabatic localized func-

tions, i.e., by the spin-dependent Wannier functions

$$w_{\mathbf{T}m}(\mathbf{r}, t) \equiv w_{im}(\mathbf{r} - \mathbf{R} - \boldsymbol{\rho}_i, t) \quad (3.6)$$

of the superconducting band, as defined in Eq. (A22) of Ref. [1]. The vectors $\mathbf{T} = \mathbf{R} + \boldsymbol{\rho}_i$ stand for the positions of the relevant atoms, $\mathbf{r}$ and t are the local and spin coordinate, respectively, and m denotes the quantum number of the crystal spin in the purely electronic system.

Within the nonadiabatic system, the crystal spin is a conserved quantity. Thus, also H^0 conserves the crystal spin of the localized states,

$$[H^0, M(\alpha)] = 0 \quad \text{for } \alpha \in G_M. \quad (3.7)$$

The purely electronic system (represented by H^0) is not coupled to boson excitations that would be able to store temporarily spin-angular momenta. Hence, H^0 also conserves the electron spin,

$$[H^0, S(\alpha)] = 0 \quad \text{for } \alpha \in O(3). \quad (3.8)$$

Consequently, the ground state $|G^0\rangle$ of H^0 satisfies the equations

$$M(\alpha)|G^0\rangle = |G^0\rangle \quad \text{for } \alpha \in G_M \quad (3.9)$$

and

$$S(\alpha)|G^0\rangle = |G^0\rangle \quad \text{for } \alpha \in O(3). \quad (3.10)$$

In a superconducting band, a randomly chosen N -electron state will generally not comply with *both* conditions (3.9) and (3.10) because the Bloch states $|\mathbf{k}, m\rangle$ with crystal spin m have $\mathbf{k}$ -dependent spin directions,

$$c_{\mathbf{k}qm}^\dagger = \sum_{s=-\frac{1}{2}}^{+\frac{1}{2}} f_{sm}^*(q, \mathbf{k}) c_{\mathbf{k}qs}^\dagger. \quad (3.11)$$

The fermion operators $c_{\mathbf{k}qm}^\dagger$ and $c_{\mathbf{k}qs}^\dagger$ create Bloch electrons with crystal spin m and spin s , respectively, and wave vector $\mathbf{k}$ in the q th branch of the superconducting band. The coefficients $f_{sm}(q, \mathbf{k})$ determine the direction of the electron spin in the Bloch state $|\mathbf{k}, m\rangle$ and, consequently, form a unitary two-dimensional matrix depending on $\mathbf{k}$ and q . In a superconducting band, the matrix $f_{sm}(q, \mathbf{k})$ cannot be chosen to be independent of $\mathbf{k}$. Thus, only very special, if any, N -electron states comply with both conditions (3.9) and (3.10).

Indeed, there exist states complying with both conditions. Let be $|G^0\rangle$ a linear combination of states

$$|Cp\rangle = \beta_{\mathbf{k}_1 q_1}^\dagger \beta_{\mathbf{k}_2 q_2}^\dagger \beta_{\mathbf{k}_3 q_3}^\dagger \cdots \beta_{\mathbf{k}_{N/2} q_{N/2}}^\dagger |0\rangle, \quad (3.12)$$

where the new operators

$$\beta_{\mathbf{k}q}^\dagger = c_{\mathbf{k}qm}^\dagger c_{-\mathbf{k}q-m}^\dagger - c_{\mathbf{k}q-m}^\dagger c_{-\mathbf{k}qm}^\dagger \quad (3.13)$$

create symmetrized Cooper pairs.

From Eq. (3.13) it follows immediately that

$$M(\alpha)\beta_{\mathbf{k}q}^\dagger M^{-1}(\alpha) = \beta_{\mathbf{k}q}^\dagger \quad \text{for } \alpha \in G_M, \quad (3.14)$$

because the operators $\beta_{\mathbf{k}q}^\dagger$ form basis functions of the identity representation Γ_1 of G_M . Thus, we have

$$M(\alpha)|Cp\rangle = |Cp\rangle \quad \text{for } \alpha \in G_M, \quad (3.15)$$

and, hence, Eq. (3.9) is true. Transforming the operators $\beta_{\mathbf{k}q}^\dagger$ in Eq. (3.13) into the s representation, we obtain again Cooper pairs of the same form,

$$\beta_{\mathbf{k}q}^\dagger = c_{\mathbf{k}qs}^\dagger c_{-\mathbf{k}q-s}^\dagger - c_{\mathbf{k}q-s}^\dagger c_{-\mathbf{k}qs}^\dagger, \quad (3.16)$$

demonstrating that also Eq. (3.10) is valid.

Eq. (3.16) can be deduced from Eq. (3.13) using Eq. (3.11) and the time-inversion symmetry of the crystal spin,

$$K c_{\mathbf{k}qm}^\dagger K^{-1} = v(m) c_{-\mathbf{k}q-m}^\dagger, \quad (3.17)$$

and of the electron spin,

$$K c_{\mathbf{k}qs}^\dagger K^{-1} = v(s) \cdot c_{-\mathbf{k}q-s}^\dagger, \quad (3.18)$$

where K denotes the operator of time inversion and

$$v(\pm\frac{1}{2}) = \pm 1.$$

The ground state $|G^0\rangle$ of H^0 complies with both conditions (3.9) and (3.10) only if the electrons form Cooper pairs invariant under time-inversion. This important result demonstrates that the nonadiabatic spin-boson interaction H_{Cb}^{ns} in Eq. (3.2) forces the electrons in a novel way to form Cooper pairs below a certain transition temperature. The formation of Cooper pairs is a consequence of the interplay of two conservation laws, namely of the conservation of the electron spin and of the conservation of the crystal spin of the localized states.

3.3. Constraining forces required for superconducting eigenstates

To date, it is not possible to solve the Schrödinger equation for the electron-boson system in a solid state. Hence, it cannot be excluded that there exists a condition for superconducting *eigenstates* not yet considered in the theory of superconductivity.

From the conditions (3.7) and (3.8) it follows that the interaction term of the electronic Hamiltonian H^0 in Eq. (3.5) has the form

$$H_{Cb}^0 = \sum_{\mathbf{k}q, \mathbf{k}'q'} \langle \mathbf{k}, q | H_{Cb}^0 | \mathbf{k}', q' \rangle \beta_{\mathbf{k}q}^\dagger \beta_{\mathbf{k}'q'} \quad (3.19)$$

showing that H_{Cb}^0 is strongly $\mathbf{k}$ and s dependent since

$$\langle \mathbf{k}_1, s_1, q_1; \mathbf{k}_2, s_2, q_2 | H_{Cb}^0 | \mathbf{k}'_1, s'_1, q'_1; \mathbf{k}'_2, s'_2, q'_2 \rangle = 0 \quad (3.20)$$

for $\mathbf{k}_1 \neq -\mathbf{k}_2$, $\mathbf{k}'_1 \neq -\mathbf{k}'_2$, $s_1 \neq -s_2$, or $s'_1 \neq -s'_2$.

This Eq. (3.20) may be interpreted as *condition of constraint* indicating the existence of *constraining forces* in a narrow superconducting band. Thus, Eq. (3.20) demonstrates that H^n is acting in a special part of the Hilbert space representing a nonadiabatic system in which constraining forces are effective in a way familiar from classical mechanics. Below a transition temperature, these constraining forces reduce the degrees of freedom of the electron system by forcing the electrons to form pairs that are invariant under time inversion, i.e., by forcing the electrons to form Cooper pairs possessing only half the degrees of freedom of unpaired electrons.

In materials that do not possess a superconducting band, on the other hand, constraining forces halving the degrees of freedom of the electrons do not exist. In the classical mechanics, however, any reduction of the degrees of freedom of any system of particles is caused by constraining forces. Hence, it cannot be excluded that also in quantum mechanical systems any reduction of the electronic degrees of freedom is produced by constraining forces since quantum particles behave in some respects similar to classical particles. This comparison of the quantum system with a classical system suggests that the constraining forces characterized by Eq. (3.20) *are required* for the formation of Cooper pairs, i.e., they are required for the Hamiltonian to possess superconducting eigenstates. This interpretation is corroborated by the observation that materials not possessing a narrow, partly filled superconducting band do not become superconducting. Thus, the author proposes that materials which do not possess a narrow, partly filled superconducting band, do not become superconducting even if the electrons of the considered material are (weakly or strongly) coupled by an effective electron-electron interaction.

It should be noted that the purely electronic system represented by the Hamiltonian H^0 in Eq. (3.5) only approximates the true nonadiabatic system represented by the operator H^n given in Eq. (3.4). So, the Cooper pairs are not really *rigid* as suggested by the ground state $|G^0\rangle$ of H^0 . In the nonadiabatic system the physics of the mechanism of constraining forces may be demonstrated more realistically in terms of “spring-mounted” Cooper pairs [17].

3.4. Calculation of the transition temperature

In accordance with the generally accepted and experimentally corroborated concept of superconductivity, the formation of Cooper pairs is mediated by Boson excitations also within a superconducting band. Further, the constraining forces determined by Eq. (3.20) do not alter the energy of the electron system but only lower the degrees of freedom of the electrons. Consequently, the vast majority of the statements and calculations of the traditional theory of superconductivity *should stay valid* in a

TABLE I: Character tables of the single-valued irreducible representations of the space group $P6/mmm = \Gamma_h D_{6h}^1$ (191) of MgB_2 , as determined from Table 5.7 in the textbook of Bradley and Cracknell [19]. ($j = 1, 2, 3$.)

$\Gamma(000), A(00\frac{1}{2})$												
	E	$C_3^\pm$	C_{2j}'	C_2	$C_6^\pm$	C_{2j}''	I	$S_6^\pm$	σ_{dj}	σ_h	$S_3^\pm$	σ_{vj}
$\Gamma_1^\pm$	$A_1^\pm$	1	1	1	1	1	1	± 1	± 1	± 1	± 1	± 1
$\Gamma_2^\pm$	$A_2^\pm$	1	1	-1	1	1	-1	± 1	± 1	∓ 1	± 1	∓ 1
$\Gamma_3^\pm$	$A_3^\pm$	1	1	1	-1	-1	-1	± 1	± 1	± 1	∓ 1	∓ 1
$\Gamma_4^\pm$	$A_4^\pm$	1	1	-1	-1	-1	1	± 1	± 1	∓ 1	∓ 1	± 1
$\Gamma_5^\pm$	$A_5^\pm$	2	-1	0	-2	1	0	± 2	∓ 1	0	∓ 2	± 1
$\Gamma_6^\pm$	$A_6^\pm$	2	-1	0	2	-1	0	± 2	∓ 1	0	± 2	∓ 1

$H(\frac{1}{3}\frac{2}{3}\frac{1}{2}), K(\frac{1}{3}\frac{2}{3}0)$							
	E	σ_h	$S_3^\pm$	$C_3^\pm$	C_{2j}''	σ_{dj}	
H_1	K_1	1	1	1	1	1	1
H_2	K_2	1	1	1	1	-1	-1
H_3	K_3	1	-1	-1	1	1	-1
H_4	K_4	1	-1	-1	1	-1	1
H_5	K_5	2	2	-1	-1	0	0
H_6	K_6	2	-2	1	-1	0	0

$M(0\frac{1}{2}0), L(0\frac{1}{2}\frac{1}{2})$								
	E	C_2	C_{21}''	C_{21}'	I	σ_h	σ_{v1}	σ_{d1}
$M_1^\pm$	$L_1^\pm$	1	1	1	1	± 1	± 1	± 1
$M_2^\pm$	$L_2^\pm$	1	-1	1	-1	± 1	∓ 1	± 1
$M_3^\pm$	$L_3^\pm$	1	1	-1	-1	± 1	± 1	∓ 1
$M_4^\pm$	$L_4^\pm$	1	-1	-1	1	± 1	∓ 1	± 1

superconducting band. In particular, the superconducting transition temperature T_c may be calculated also in a superconducting band by a slightly modified BCS equation [18] in the weak-coupling limit [15]. A calculation of T_c within the NHM in the strong-coupling limit remains to be done. Principally, however, the group-theoretical NHM does not provide methods to calculate the matrix elements of H_{Cb}^0 in Eq. (3.19). Hence, it does not distinguish between weak-coupling and strong-coupling superconductivity. It only proposes that the equation of constraint (3.20) is a universal condition for superconducting eigenstates in the weak-coupling as well as in the strong-coupling limits.

4. SUPERCONDUCTING BAND IN MgB_2

We show now that the energy band denoted in Fig. 1 by the bold line is a superconducting band. It is labeled by the representations

$$\Gamma_5^-, \Gamma_6^+; K_6; M_3^-, M_2^+; A_5^+, A_6^-; L_1^+, L_4^-; H_5. \quad (4.1)$$

Table IV (a) lists all the four bands in MgB_2 whose Bloch functions can be unitarily transformed into

TABLE II: Character tables of the double-valued irreducible representations of the space group $\Gamma_h D_{6h}^1$ of MgB_2 , as determined from Table 6.13 of Bradley and Cracknell [19]. ($j = 1, 2, 3$.)

$\Gamma(000), A(00\frac{1}{2})$										
	E	$\bar{E}$	$C_6^\pm$	$\bar{C}_6^\pm$	$C_3^\pm$	$\bar{C}_3^\pm$	C_2	$\bar{C}_2$	C_{2j}'	$\bar{C}_{2j}''$
$\Gamma_7^\pm$	$A_7^\pm$	2	-2	0	0	-2	2	0	0	0
$\Gamma_8^\pm$	$A_8^\pm$	2	-2	$\sqrt{3}$	$-\sqrt{3}$	1	-1	0	0	0
$\Gamma_9^\pm$	$A_9^\pm$	2	-2	$-\sqrt{3}$	$\sqrt{3}$	1	-1	0	0	0

$\Gamma(000), A(00\frac{1}{2})$ (continued)										
	I	$\bar{I}$	$S_3^\pm$	$\bar{S}_3^\pm$	$S_6^\pm$	$\bar{S}_6^\pm$	$\bar{\sigma}_h$	$\bar{\sigma}_{dj}$	$\bar{\sigma}_{vj}$	
$\Gamma_7^\pm$	$A_7^\pm$	± 2	∓ 2	0	0	∓ 2	± 2	0	0	0
$\Gamma_8^\pm$	$A_8^\pm$	± 2	∓ 2	$\pm\sqrt{3}$	$\mp\sqrt{3}$	± 1	∓ 1	0	0	0
$\Gamma_9^\pm$	$A_9^\pm$	± 2	∓ 2	$\mp\sqrt{3}$	$\pm\sqrt{3}$	± 1	∓ 1	0	0	0

$H(\bar{1}\frac{2}{3}\frac{1}{2}), K(\bar{1}\frac{2}{3}0)$										
	E	$\bar{E}$	$S_3^\pm$	$\bar{S}_3^\pm$	$C_3^\pm$	$\bar{C}_3^\pm$	$\bar{\sigma}_h$	$\bar{C}_{2j}''$	$\bar{\sigma}_{dj}$	
H_7	K_7	2	-2	0	0	-2	2	0	0	0
H_8	K_8	2	-2	$\sqrt{3}$	$-\sqrt{3}$	1	-1	0	0	0
H_9	K_9	2	-2	$-\sqrt{3}$	$\sqrt{3}$	1	-1	0	0	0

$M(0\frac{1}{2}0), L(0\frac{1}{2}\frac{1}{2})$										
	E	$\bar{E}$	C_2	$\bar{C}_2$	C_{21}'	$\bar{C}_{21}''$	I	$\bar{I}$	$\bar{\sigma}_h$	$\bar{\sigma}_{v1}$
$M_5^\pm$	$L_5^\pm$	2	-2	0	0	0	± 2	∓ 2	0	0

symmetry-adapted and best localized Wannier functions situated on the B atoms. Each band consists of two branches because there are two B atoms in the unit cell. While the representations (4.1) coincide with the representations of band 4 in Table IV (a) at points L, M, K , and H , the representations at points Γ and A are different. Hence, we *cannot* represent the Bloch functions of this band by symmetry-adapted and best localized (spin-independent) Wannier functions centered on the B sites.

The situation is changed when we replace the single-valued representations $R_i^\pm$ by the corresponding double-valued representations $R_i^\pm \times D_{1/2}$ listed in Table III. The energy band with the representations (4.1) now is characterized by the double-valued representations

$$\Gamma_7^-, \underline{\Gamma_8^-}, \Gamma_7^+, \underline{\Gamma_9^+}; \underline{K_7}, \underline{K_8}; \underline{M_5^-}, \underline{M_5^+}; \underline{A_7^+}, \underline{A_8^+}, \underline{A_7^-}, \underline{A_9^-}; \underline{L_5^+}, \underline{L_5^-}; \underline{H_7}, \underline{H_9}. \quad (4.2)$$

The underlined representations form band 3 in Table IV (b). Hence, the associated Bloch functions can be unitarily transformed into symmetry-adapted and best localized *spin-dependent* Wannier functions situated on the B sites.

TABLE III: Compatibility relations between the single-valued (upper row) and double-valued (lower row) representations of the space group $\Gamma_h D_{6h}^1$ of MgB_2 .

Γ, A										
$R_1^\pm$	$R_2^\pm$	$R_3^\pm$	$R_4^\pm$	$R_5^\pm$	$R_6^\pm$					
$R_8^\pm$	$R_8^\pm$	$R_9^\pm$	$R_9^\pm$	$R_7^\pm + R_8^\pm$	$R_7^\pm + R_9^\pm$					
H, K						L, M				
R_1	R_2	R_3	R_4	R_5	R_6	$R_i^\pm, i = 1, 2, 3, 4$				
R_8	R_8	R_9	R_9	$R_7 + R_9$	$R_7 + R_8$	$R_5^\pm$				

Notes to Table III

- (i) The single-valued and double-valued representations are listed in Tables I and II, respectively.
- (ii) Each column lists the double-valued representation $R_i \times D_{1/2}$ below the single-valued representation R_i .

These Wannier functions are only weakly spin dependent since they do not strongly differ from the Wannier function belonging to band 4 in Table IV (a). It is only the representations $\Gamma_4^+ + \Gamma_2^-$ and $A_1^+ + A_3^-$ of band 4 in Table IV (a) which do not belong to the representations (4.1).

Between A and L the superconducting band jumps from the upper to the lower band. This small jump is allowed within the NHM because the Bloch functions of both bands belong to the same double-valued representation and the jump does not cross the Fermi level.

5. DISCUSSION

This paper shows that the intermetallic superconducting compound MgB_2 possesses a narrow, roughly half-filled “superconducting band” in its band structure, see Fig. 1. In addition to the previous observations about elemental superconductors, non-superconductors, $\text{YBa}_2\text{Cu}_3\text{O}_7$, and La_2CuO_4 (as mentioned in Sec. 1) this result provides further evidence that superconducting bands are a general feature of both weak-coupling and strong-coupling superconductors. Hence, the author proposes that in any material Cooper pairs are stabilized by the constraining forces determined by the condition of constraint (3.20) and generated by the nonadiabatic condensation mechanism characterized by Eq. (2.3). These constraining forces are effective only in narrow superconducting bands and are proposed to be required that the Hamiltonian of the electron-boson system possesses superconducting *eigenstates*.

The symmetry of the Bloch functions of the *entire* superconducting band determines the symmetry and spin dependence of the nonadiabatic localized states. The nonadiabatic condensation mechanism characterized by Eq. (2.3), on the other hand, is produced by the Coulomb correlation energy of the electrons *near the Fermi level*,

TABLE IV: Single- and double-valued representations of all the energy bands in MgB_2 with symmetry-adapted and optimally localized (spin-dependent) Wannier functions centered at the B atoms.

(a) Single-valued representations						
	Γ	L	M	A	K	H
Band 1	$\Gamma_1^+ + \Gamma_3^-$	$L_2^+ + L_3^-$	$M_1^+ + M_4^-$	$A_4^+ + A_2^-$	K_5	H_6
Band 2	$\Gamma_2^+ + \Gamma_4^-$	$L_4^+ + L_1^-$	$M_3^+ + M_2^-$	$A_3^+ + A_1^-$	K_5	H_6
Band 3	$\Gamma_3^+ + \Gamma_1^-$	$L_3^+ + L_2^-$	$M_4^+ + M_1^-$	$A_2^+ + A_4^-$	K_6	H_5
Band 4	$\Gamma_4^+ + \Gamma_2^-$	$L_1^+ + L_4^-$	$M_2^+ + M_3^-$	$A_1^+ + A_3^-$	K_6	H_5

(b) Double-valued representations			
	Γ	M	A
Band 1	$\Gamma_7^+ + \Gamma_7^-$	$M_5^+ + M_5^-$	$A_7^+ + A_7^-$
Band 2	$\Gamma_8^+ + \Gamma_9^-$	$M_5^+ + M_5^-$	$A_9^+ + A_8^-$
Band 3	$\Gamma_9^+ + \Gamma_8^-$	$M_5^+ + M_5^-$	$A_8^+ + A_9^-$

(b) (continued)			
	L	K	H
Band 1	$L_5^+ + L_5^-$	$K_8 + K_9$	$H_8 + H_9$
Band 2	$L_5^+ + L_5^-$	$K_7 + K_9$	$H_7 + H_8$
Band 3	$L_5^+ + L_5^-$	$K_7 + K_8$	$H_7 + H_9$

Notes to Table IV

- (i) The bands 2 and 3 in Table IV (b) form superconducting bands.
- (ii) Band 1 of Table IV (b) is *not* a superconducting band because the representations $\Gamma_7^\pm$ cannot be written in the form $R \times D_{1/2}$ where R stands for any one-dimensional single-valued representation and $D_{1/2}$ denotes the two-dimensional double-valued representation of the three-dimensional rotation group $O(3)$. The form $R \times D_{1/2}$ of the representations $\Gamma_8^\pm$ and $\Gamma_9^\pm$ belonging to bands 2 and 3 in Table IV (b) ensures that the spin-dependent Wannier functions transform under the space group operations like spin functions, see Eq. A(28) of Ref. [1].
- (iii) The single-valued and double-valued representations are listed in Tables I and II, respectively.
- (iv) Each row defines one band consisting of two branches, because there are two B atoms in the unit cell.
- (v) The bands are determined by Eq. (23) of Ref. [7].
- (vi) Assume a band of the symmetry in any row of this table to exist in the band structure of MgB_2 . Then the Bloch functions of this band can be unitarily transformed into Wannier functions that are
 - localized as well as possible;
 - centered at the B atoms; and
 - symmetry-adapted to the space group $\Gamma_h D_{6h}^1$ of MgB_2 .

These Wannier function are usual (spin-independent) Wannier function if the considered band is characterized by the single-valued representations (a). They are spin dependent if the band is characterized by the double-valued representations (b).

in accordance with the generally accepted concept that correlated conduction electrons are responsible for superconductivity.

Further, in accordance with the general belief, also in superconducting bands the formation of Cooper pairs is mediated by boson excitations. In superconducting bands, however, the pair formation is mediated by the *energetically lowest* boson excitations of the crystal that possess the crystal-spin angular momentum $1 \cdot \hbar$ and are sufficiently stable to transport it through the crystal. These “crystal-spin-1” bosons are localized excitations $|\mathbf{T}, l\rangle$ (with $l = -1, 0, +1$ labeling the three directions of the crystal spin and $\mathbf{T}$ denoting a lattice point) of well-defined symmetry [14, 20] which propagate as Bloch waves (with the crystal momentum $\hbar \cdot \mathbf{k}$) through the crystal.

The $|\mathbf{T}, l\rangle$ are generated during spin-flip processes in the superconducting band and must carry off the surplus crystal-spin angular-momenta generated at these processes. This spin-boson mechanism suggests that the $|\mathbf{T}, l\rangle$ are coupled phonon-plasmon modes: In a first step the atomic-like electrons in the superconducting band transmit their angular momenta to the core electrons by generating a plasmon-like vibration of the core electrons against the atoms. In a second step, these plasmon-like excitations generate phonon-like vibrations of lower energy if crystal-spin-1 phonons are sufficiently stable in the considered material.

Thus, the author proposes that the $|\mathbf{T}, l\rangle$ are coupled phonon-plasmon modes which have dominant phonon character in the isotropic lattices of the transition elements and, hence, confirm the electron-phonon mechanism that enters the BCS theory [18] in these materials [14]. However, phonon-like excitations are not able to transport crystal-spin angular-momenta within the two-dimensional copper-oxygen layers of the cuprates, see Ref. [20] for preliminary ideas to this problem. Within two-dimensional layers, the $|\mathbf{T}, l\rangle$ necessarily are energetically higher lying excitations of dominant plasmon character. This clear dependence of stable crystal-spin-1 bosons on the properties of the lattice suggests that they are (at least partially) responsible for the special properties of the layered superconductors, i.e., their strong-coupling features and their high transition temperatures.

Also MgB_2 contains two-dimensional hexagonal nets of B atoms. Thus, also in this layered material crystal-spin-1 *phonons* will be less stable than in the isotropic lattices of the transition elements. The balance between the phonon and plasmon character of stable crystal-spin-1 excitations is shifted towards the plasmon character leading to a higher transition temperature and to the experimentally established [21, 22, 23] reduced isotope effect.

The superconducting band in MgB_2 is composed of σ - and π -bands in accordance with the two-band model of superconductivity [24, 25] in this material characterized by σ - and π -bands associated with different parts of the Fermi surface [26]. The part of the Fermi surface of the

superconducting band enclosing the points Γ and A has σ character, the other parts have π character.

In the band structures of the two-dimensional superconductors $\text{YBa}_2\text{Cu}_3\text{O}_7$ [10], MgB_2 (this paper), and La_2CuO_4 [7] I found a new feature of the superconducting bands: the related spin-dependent Wannier functions are only *weakly* spin dependent. I believe that this weak spin dependence is an additional condition for stable two-dimensional high- T_c superconducting states. This question requires further theoretical consideration and further examination of the band structures of high- T_c supercon-

ductors.

Acknowledgments

I am indebted to Ove Jepsen for providing me with the band-structure data of MgB_2 . I thank Horst Strunk for his support of my work and Ernst Helmut Brandt for critical and helpful comments on the manuscript.

-
- [1] E. Krüger, Phys. Rev. B **63**, 144403 (2001).
 - [2] W. Heisenberg, Z. Phys. **49**, 619 (1928).
 - [3] N. F. Mott, Can. J. Phys. **34**, 1356 (1956).
 - [4] J. Hubbard, Proc. R. Soc. London, Ser. A **276**, 238 (1963).
 - [5] E. Krüger, Phys. Rev. B **40**, 11090 (1989).
 - [6] E. Krüger, Phys. Rev. B **59**, 13795 (1999).
 - [7] E. Krüger, J. Supercond. **18**(4), 433 (2005).
 - [8] E. Krüger, Phys. Rev. B **75**, 024408 (2007).
 - [9] E. Krüger, Phys. Status Solidi B **85**, 493 (1978).
 - [10] E. Krüger, arXiv:0704.2110 (2007).
 - [11] E. Krüger, J. Supercond. **14**(4), 551 (2001).
 - [12] J. Nagamatsu, N. Nakagawa, T. Muranaka, Y. Zenitani, and J. Akimitsu, Nature (London) **410**, 63 (2001).
 - [13] With free atoms, the nonadiabatic motion of the nuclei occurs in such a way that the total centre of mass stays at rest. In a solid state, consisting of bound atoms, this restriction does not hold.
 - [14] E. Krüger, Phys. Rev. B **30**, 2621 (1984).
 - [15] E. Krüger, J. Supercond. **14**(4), 469 (2001), it should be noted that in this paper the term “superconducting band” was abbreviated by “ σ -band”.
 - [16] O. Jepsen, private communication.
 - [17] E. Krüger, J. Supercond. **15**(2), 105 (2002).
 - [18] J. Bardeen, L. N. Cooper, and J. R. Schrieffer, Phys. Rev. **108**, 1175 (1957).
 - [19] C. Bradley and A.P. Cracknell, *The Mathematical Theory of Symmetry in Solids* (Clarendon, Oxford, 1972).
 - [20] E. Krüger, Phys. Status Solidi B **156**, 345 (1989).
 - [21] D. G. Hinks, H. Claus, and J. D. Jorgensen, Nature (London) **411**, 457 (2001).
 - [22] S. L. Bud’ko, G. Lapertot, C. Petrovic, C. E. Cunningham, N. Anderson, and P. C. Canfield, Phys. Rev. Lett. **86**, 1877 (2001).
 - [23] P. Brotto, M. Tropeano, C. Ferdeghini, P. Manfrinetti, A. Palenzona, E. Galleani d’Agliano, and M. Putti, Phys. Rev. B **78**, 092502 (2008).
 - [24] A. E. Koshelev, A. A. Varlamov, and V. M. Vinokur, Phys. Rev. B **72**, 064523 (2005), and references therein.
 - [25] I. I. Mazin, O. K. Andersen, O. Jepsen, O. V. Dolgov, J. Kortus, A. A. Golubov, A. B. Kuz’menko, and D. van der Marel, Phys. Rev. Letters **89**, 107002 (2002).
 - [26] I. I. Mazin, O. K. Andersen, O. Jepsen, A. A. Golubov, O. V. Dolgov, and J. Kortus, Phys. Rev. B **69**, 056501 (2004).